

U.S.S.N. 09/785,593

Filed: February 16, 2001

AMENDMENT AND RESPONSE TO OFFICE ACTION

In the Claims

1. (currently amended) A resorbable interbody spinal fusion device for spinal fixation, said device comprising an interbody spinal fusion device comprising

(1) between 25 and 100% of a biocompatible, bioerodible polymer producing which produces acidic products or low molecular weight resorbable fragments upon hydrolytic degradation, wherein the polymer comprises a strengthening material selected from the group consisting of crosslinked monomers, reinforcing fibers, self-reinforcing aligned fibers of the polymer, degradable polymeric scaffolds, and interpenetrating networks,

(2) one or more void spaces, and

(3) a buffering or neutralizing agent,

wherein one or more of the void spaces ~~contains~~ comprises a grafting material for facilitating bony development ~~and/or~~ spinal fusion.

Claims 2-3. (canceled)

4. (previously presented) The resorbable interbody spinal fusion device of claim 1, wherein said grafting material is an autologous grafting material.

5. (withdrawn) The resorbable interbody spinal fusion device of claim 1, wherein said device is shaped substantially as a tapered wedge or cone.

6. (original) The resorbable interbody spinal fusion device of claim 1, wherein said device is shaped substantially as a threaded screw.

U.S.S.N. 09/785,593

Filed: February 16, 2001

AMENDMENT AND RESPONSE TO OFFICE ACTION

7. (withdrawn) The resorbable interbody spinal fusion device of claim 1, wherein said device is shaped substantially as a threaded rod of cruciform configuration.

8. (withdrawn) The resorbable interbody spinal fusion device of claim 5, further comprising at least one serrated or threaded outer face.

Claims 9-10. (canceled)

11. (currently amended) The resorbable interbody spinal fusion device of claim 1, wherein said ~~resorbable material is a polymer~~ or reinforcing material is selected from the group consisting of polydioxanone, poly(ϵ -caprolactone), polyanhydride, polyester, copoly(ether-ester), polyamide, polylactone, poly(propylene fumarate), and combinations thereof.

12. (original) The resorbable interbody spinal fusion device of claim 11, wherein said bioerodible polymer comprises poly(lactide-co-glycolide) with a lactide to glycolide ratio in the range of 0:100% to 100:0% inclusive.

13. (currently amended) The resorbable interbody spinal fusion device of claim 10 ~~1~~, wherein said buffering or neutralizing agent is a polymer comprising at least one basic group.

14. (currently amended) The resorbable interbody spinal fusion device of claim 13, wherein said polymer ~~comprising~~ comprises at least one basic group is selected from the group consisting of polyamines, polyesters, vinyl polymers, and copolymers of acrylic acid.

15. (currently amended) The resorbable interbody spinal fusion device of claim 10 ~~1~~, wherein said buffering or neutralizing agent is a compound that, on exposure to water, hydrolyzes to form a base.

43043501v1

5

CST 112 CON
07704400013

U.S.S.N. 09/785,593

Filed: February 16, 2001

AMENDMENT AND RESPONSE TO OFFICE ACTION

16. (previously presented) The resorbable interbody spinal fusion device of claim 1, wherein said buffering or neutralizing agent is selected from the group consisting of carbonates, phosphates, acetates, succinates and citrates.

17. (currently amended) The resorbable interbody spinal fusion device of claim 1 wherein said ~~resorbable material~~ polymer further comprises reinforcing fibers.

18. (currently amended) The resorbable interbody spinal fusion device of claim 17, wherein said reinforcing fibers are made of said ~~resorbable~~ polymer.

19. (canceled)

20. (previously presented) The resorbable interbody spinal fusion device of claim 17, wherein said reinforcing fibers are made of said buffering or neutralizing agent.

Claims 21 - 23. (canceled)

24. (currently amended) The resorbable interbody spinal fusion device of claim ~~10~~ 1, wherein said buffering or neutralizing agent is selected from the group consisting of compounds wherein the pKa of the conjugate acids of said compounds is greater than the pKa of acids produced by hydrolysis of the ~~polymer(s)~~ polymer ~~from which said device is prepared~~.

25. (currently amended) The resorbable interbody spinal fusion device of claim 1, wherein said device is fabricated from at least two ~~resorbable~~ bioerodible polymers.

26. (currently amended) The resorbable interbody spinal fusion device of claim 25, wherein one of said ~~resorbable~~ polymers is poly (propylene fumarate) which acts as a reinforcing material.

45048501v1

6

CSI 112 CON
07704400013

U.S.S.N. 09/785,593

Filed: February 16, 2001

AMENDMENT AND RESPONSE TO OFFICE ACTION

27. (currently amended) The resorbable interbody spinal fusion device of claim 25, wherein one of said ~~resorbable~~ polymers has been cross-linked in the presence of a crosslinking agent and an initiator, whereby said crosslinked ~~resorbable~~ polymer forms a reinforcing interpenetrating network.

28. (currently amended) The resorbable interbody spinal fusion device of claim 25, wherein one of said at least two ~~resorbable~~ polymers has been cross-linked in the presence of vinyl pyrrolidone as a crosslinking agent and an initiator.

29. (currently amended) The resorbable interbody spinal fusion device of claim 25, wherein one of said at least two ~~resorbable~~ polymers has been cross-linked in the presence of a crosslinking agent and benzoyl peroxide as an initiator.

30. (original) The resorbable interbody spinal fusion device of claim 1, wherein said device is fabricated from a polymer wherein molecular chains of said polymer have been aligned to be essentially parallel.

31. (original) The resorbable interbody spinal fusion device of claim 30, wherein said device has been cut such that the aligned polymer molecular chains are at approximately a 45° angle to a surface of said device.

32. (canceled)

33. (previously presented) The resorbable interbody spinal fusion device for spinal fixation of claim 1, wherein said buffering or neutralizing agent is hydroxyapatite.

34. (canceled)

45041501v1

7

CST 112 CON
077044/00013